

Technical Data Sheet : P16

Material	Polytetrafluoroethylene
General Qualities	P16 is a virgin PTFE fine powder suitable for paste extrusion. The material is made using the dispersion process without PFOA. It has excellent chemical stability, electrical and mechanical properties. The material is deal for thick-wall tubing and hose and rod.
Packaging Storage and Transport	Sealed in PVC bags inside waterproof fibre tub. 25±0.1kg per barrel net weight. Fully certificated. Store in clean, dry warehouse. Avoid excessive heat, cold, moisture, and rough handling.

Material Properties	Testing according to ASTM D 4895		
Tensile Strength		≥28.0	MPa
Elongation at Break		≥330	%
Bulk Density		480±100	g/l
Material Density		2.19±0.2	g/cc
Particle Size D50		500±100	µm
Water Content		≤0.3	%
Extrusion Pressure		30±10	MPa @ RR 400:1
Maximum Reduction Ratio		1600:1	
Melting Point	First	327±5	°C
	Second	342±5	°C

Safety	If heating above 260 °C, small amounts of decomposition products can fume. Avoid inhalation of these fumes. Processing equipment and surrounding area should be adequately ventilated. Smoking must be avoided. Avoid eye contact. If this happens, irrigate immediately and seek medical advice. It is best to also avoid skin contact. If this happens, wash with soap and water. When cleaning equipment, do not burn off with flame or furnace.
---------------	---